

TECHNICAL INFORMATION

DRYING OF TOPFLOW SCREED A

In common with other screeds, it is very important that good drying conditions are provided as soon as it is appropriate. For Topflow Screed A adequate protection from rapid drying or draughts should be provided for the first 48-72 hours, but thereafter the relative humidity of the building should be low to allow moisture release from the screed and facilitate drying. Failure to provide the desired conditions can prolong screed drying times considerably and may lead to delays in the construction schedule.

SCREED DRYING TIME

Under ideal drying conditions (a well ventilated room) Topflow Screed A dries at a rate of 1mm/day up to a thickness of 40mm, and then at a rate of 0.5mm/day for thicknesses above this.

FOR EXAMPLE

50mm Topflow Screed A drying time:
(40mm x 1mm per day) + (10mm x 0.5mm per day) = 60 Days (2 months) (Guidance only).

NB: Drying of screeds can be greatly influenced by individual site conditions.

Drying times can be reduced by provision of good ventilation by opening windows and doors, the use of dehumidifiers and commissioning of underfloor heating systems to manufacturers' guidelines and recommendations.

ASSISTED DRYING TIME DEHUMIDIFIERS

Dehumidifiers can be used as early as 72 hours after the placing of Topflow Screed A to assist with drying. It is important that a closed system is employed to ensure that any moisture extracted from the environment during operation is removed. Any water collected should be removed regularly. We suggest the use of industrial closed-circuit systems.

FORCE DRYING

- Force drying of Topflow Screed A can begin as early as seven days following installation of the screed by various methods
- Commissioning (heating and cooling procedure) of underfloor heating systems. Set flow temperature to 20-25°C, maintain for a minimum of 24 hours and then gradually increase the temperature in 5°C increments to maximum operating temperature. This should be maintained for a further seven days (water temperature should not exceed 55°C for screeds), prior to returning to ambient temperature again in 5°C increments. Then the system should be turned off for 48 hours prior to moisture testing of the screed
- Space heaters and dehumidifiers in combination. Fossil fuel fired heaters (e.g. gas heaters) must be avoided as they will raise humidity

IMPORTANT

After drying the screed, the residual moisture content must be determined using one of the approved test methods - hair hygrometer, carbide bomb or oven dry tests to demonstrate suitability for acceptance of floor finishes.

NB: Drying of screeds can be greatly influenced by individual site conditions.

For more details contact

0800 1218 218

enquiries@tarmac.com

topflowscreeda@tarmac.com

The information given in this technical data sheet is based on our current knowledge and is intended to provide general notes on our products and their uses. Tarmac endeavour to ensure that the information given is accurate, but accept no liability for its use or its suitability for particular application because of the product being used by the third party without our supervision. Any existing intellectual property right must be observed.